

Tel: +44 (0) 1706 869777 E-mail: sales@desal.co.uk Web: www.desal.co.uk

Introduction

Properties

Hydraulic

Suggested

Operating

Conditions

For more information about DOW™ resins, call the Dow Water & Process Solutions business:

Characteristics

North America: 1-800-447-4369
Latin America: (+55) 11-5188-9222
Europe: +800-3-694-6367
Italy: +800-783-825
South Africa: +0800 99 5078
Pacific: +8007776 7776
China: +400 889-0789
http://www.dowwaterandprocess.com



Form No. 177-03049-0313

AMBERLITE™ IRA67

Industrial Grade Weak Base Anion Exchanger

AMBERLITE IRA67 resin is a weak base anion exchange resin with a gel type acrylic matrix. It has a high capacity, excellent physical stability, fast kinetics, outstanding resistance to organic fouling and basicity higher than that of polystyrenic weak base resins.

The flexible acrylic structure of AMBERLITE IRA67 resin allows for effective adsorption and desorption of naturally occurring organic molecules, such as humic and fulvic acids, that are present in many water supplies.

Physical form	Translucent white spherical beads
Matrix	Crosslinked acrylic gel structure
Functional group	Tertiary amine
lonic form as shipped	Free Base (FB)
Total exchange capacity	≥ 1.60 eq/L (FB form)
Moisture holding capacity	56 to 64 % (FB form)
Shipping weight	700 g/L
Particle Size	
Uniformity coefficient	≤ 1.80
Harmonic mean size	0.500 – 0.750 mm
	< 0.300 mm
	3.0 % max
Reversible swelling	FB → Cl ⁻ ≤ 30 %

Maximum operating temperature 60°C 700 mm Minimum bed depth 5 to 40 BV*/h Service flow rate Regeneration NaOH Regenerant 130 % of ionic load Level Concentration 2 to 4 % 30 minutes Minimum contact time Slow rinse 2 BV at regeneration flow rate 8 to 16 BV at 10 BV/h Fast rinse

AMBERLITE IRA67 resin gives a pressure drop of about 18 kPa/m bed depth per 10 m/h at 15 °C. A backwash flow rate of 4 m/h gives a bed expansion of about 65 % at 15 °C.

Notice: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

