



Tel: +44 (0) 1706 869777
 E-mail: sales@desal.co.uk
 Web: www.desal.co.uk

DOWEX™ MONOSPHERE™ C-350

Uniform Particle Size, Strong Acid Cation Exchange Resin for Applications with High Salt Efficiency

Product	Type	Matrix	Functional group
DOWEX™ MONOSPHERE™ C-350	Strong acid cation	Polystyrene-DVB, gel	Sulfonic acid

Guaranteed Sales Specifications		Na ⁺ form
Total exchange capacity, min.	eq/L	2.2
	kgr/ft ³ as CaCO ₃	48.2
Water content	%	38 – 45
Bead size distribution		
Mean particle size	µm	350 ± 50
Uniformity coefficient, max.		1.1
< 200 µm, max.	%	0.5

Typical Physical and Chemical Properties		Na ⁺ form
Whole uncracked beads	%	95 - 100
Particle density	g/mL	1.30
Shipping weight**	g/L	830
	lbs/ft ³	51
Total swelling (Ca ⁺⁺ → Na ⁺)	%	4

Recommended Operating Conditions	• Maximum operating temperature	130°C (265°F)
	• pH range	0 - 14
	• Bed depth, min.	200 mm (0.7 ft)
	• Flow rates:	
	Service/fast rinse	5 - 200 m/h (2 - 80 gpm/ft ²)
	Backwash	See Figure 1
	Regeneration/displacement rinse	5 - 20 m/h (2 - 8 gpm/ft ²)
• Total rinse requirement	2 - 5 Bed volumes	
• Regenerant:		
Type	5 - 25% NaCl	

** As per the backwashed and settled density of the resin, determined by ASTM D-2187.

Typical Properties and Applications

DOWEX™ MONOSPHERE™ C-350 resin is a uniform particle size gel cation resin. The small beads yield an outstanding operating capacity, which in turn results in a high regeneration efficiency.


DOWEX MONOSPHERE C-350 resin has excellent mechanical strength and very good stability to oxidation.

Packaging

25 liter bags or other packaging upon request

Figure 1. Backwash Expansion Data

Temperature = 20° C (68° F)




For other temperatures use:

$$F_T = F_{77°F} [1 + 0.008 (T_F - 77)], \text{ where } F \equiv \text{gpm/ft}^2$$

$$F_T = F_{25°C} [1 + 0.008 (1.8T_C - 45)], \text{ where } F \equiv \text{m/h}$$

Figure 2. Pressure Drop Data

Temperature = 20° C (68° F)



For other temperatures use:

$$P_T = P_{20°C} / (0.026 T_C + 0.48), \text{ where } P \equiv \text{bar/m}$$

$$P_T = P_{68°F} / (0.014 T_F + 0.05), \text{ where } P \equiv \text{psi/ft}$$

Note: These resins may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

DOWEX™ Ion Exchange Resins

For more information about DOWEX resins, call the Dow Water Solutions business:

North America: 1-800-447-4369
 Latin America: (+55) 11-5188-9222
 Europe: (+32) 3-450-2240
 Pacific: +60 3 7958 3392
 Japan: +813 5460 2100
 China: +86 21 2301 9000

<http://www.dowwatersolutions.com>

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

